

SARL POROTECHNIC

Zone de légrin

Route de St Gilles

30132 CAISSARGUES

Tel. 04.66.38.38.20

www.porotechnic.com

Terra Cotta

FINISHING ACRYLIC:

24 hours after the last coat of resin.

Go about things in fine and regular coats (1 - 2 hours of drying between every coat).

WITH PROCIR BRIL (ancient PR808 WARRIOR ctl): satiny finishing

- Blend dose of the catalyst $\frac{1}{2}$ with 1 can.
- The mixture not keeping in time, it is recommended to make mixture in a bucket by respecting doses (eg 1 litre of PROCIR BRIL $\frac{1}{5}$ of $\frac{1}{2}$ dose of the catalyst). Use a not downy, clean rag moisturize it beforehand, after tempering in mixture drain it without spining and applying in light fine and regular coats.

WITH PROCIR BRIGHTNESS (ancient POROPLEDGE): bright finishing.

- Pour the product into a bucket, use a not downy, clean rag moisturize it, after tempering beforehand drain it without spining and applying there light fine and regular coats.

WITH PROCIR SAT (ancient CHROMOSTAR): very satiny finishing

- Pour the product into a bucket, use a not downy, clean rag moisturize it, after tempering beforehand drain it without spining and applying there light fine and regular coats.