

## SARL POROTECHNIC

Zone de légrin

Route de St Gilles

30132 CAISSARGUES

Tel. 04.66.38.38.20

[www.porotechnic.com](http://www.porotechnic.com)

### Terra Cotta

#### SCOURING:

##### 1) New grounds:

With **PROCIDEX** (old DK 11) acid especially balanced for a scouring without aggression of the joints, diluted depending on the state of 1 liter of product for 1 liter of water with 50/50.

- To **aspire** beforehand the ground so necessary (dust).
- To **wet** the surface of the part where you will work.
- To **start** with the plinths and the edges with delimitation of a square.
- To **rinse** progressively with sponge and clear water. It is preferable to be provided with two buckets of rinsing, for wetting the square and the joint well and collecting mud, the second for finishing well and leaving Net the square and the joint (with vacuum cleaner with water, to rub with the rinsing and to aspire continuation).
- For the center of the part, to proceed by band on a depth from 2 to 4 squares according to their dimension and their porosity.
- In the event of tough residues, cement burs, adhesives, painting, to scrape as a preliminary and rub with abrasive scotch-brite if necessary.

##### 2) rounds having undergone treatments:

- Preliminary scouring with **PRODEC WAXES** (old DK FILM) to pass to the brush dilution 50%, to let work 10 to 20 minutes and to pickle with single-brush or the hand diluted with 50% according to the same process as with PROCIDEX (old DK 11)
- To rinse with PROCIDEX (old DK 11) to open the pores (dilution 50%) the cleaning of the finished ground: To let dry 8 days.