

SARL POROTECHNIC

Zone de légrin

Route de St Gilles

30132 CAISSARGUES

Tel. 04.66.38.38.20

www.porotechnic.com

Terra Cotta

OUTSIDE TREATMENT:

The cleaning being ended, after 8 days of drying.

Clear treatment:

APPLY ANTISALP proton coal equivalent CLEAR " S "

- Pulverize 2 coats of ANTISALP definitely wipe surplus (puddles) with one rag. 1st very generous coat in the morning, 2nd in the afternoon
- 24 hours after ANTISALP, to apply PROTON COAL EQUIVALENT CLEAR " S " in 2 coats in 24 hours of space. Wait 10 minutes and wipe surplus with a rag (after every coat).

Lightly revealing treatment:

APPLY ANTISALP proton coal equivalent SOLV (skated aspect)

- Pulverize 2 coats of ANTISALP definitely wipe surplus (puddles) with one rag (1 can 5 litres for 30 m²) 1st very generous coat the morning, 2nd the afternoon
- The following day to cross 2 coats of PROTON COAL EQUIVALENT SOLV to the brush wet on wet. 1st very generous, 2nd coat sleeps ½ an hour later. Wait 10 minutes and wipe surplus with a rag (after every coat).

Avoid working at the height of warmth.