

[www.porotechnic.com](http://www.porotechnic.com)

Zone de Légrin – Route de Saint-Gilles – 30132 CAISSARGUES

04.66.38.38.20 Télécopie : 04.66.38.38.21

S.A.R.L au capital de 50 000 F – SIRET 393122 882 00011

E-mail : [contact@porotechnic.com](mailto:contact@porotechnic.com)

## ITREATMENT TILES OF CEMENT:

### Cleaning:

A - on the ancient party: (In case of presence of wax)

Indistinct 4 litres of SHONE PRODEC (ancient DK FILM) in 6 litres of water.

Let act on the soil ½ an hour later have spread in the broom (pick up the residual in the vacuum cleaner with water (this is for rent!).

Put gloves.

To prepare 2 litres PRODEC apart in a bucket SHINES 2 litres water, to soak scotchbrite in resolution. Rub tile normally by tile.

Rinse every tile in the sponge 2 - 3 times.

Rinse with sour sulfamique PROCIDEX (ancient DK11) diluted in 3 % (1/2 glass for ½ bucket of water).

Let dry 3 - 4 days.

### B - On the new party:

Having wet tiles in water, passing sour PROCIDEX sulfamique (ancient DK11) with Scotchbrite diluted in ½ glass for a bucket of water. Rub normally, rinse in the sponge in water 2 - 3 times.

Let dry 3 - 4 days.

### Treatment:

With PROTON COAL EQUIVALENT SOLV (ancient POROSTAR):

Cross PROTON COAL EQUIVALENT SOLV to the spalter (broad brush to be varnished) in 2 coats.

1st generous, 2nd coat puts to bed dices drying of the 1st. (Definitely wipe if zones stay in surface ½ an hour later).

48 hours afterwards, cross 1 - 2 fine coats of PROCIR SAT (ancient CHROMOSTAR) in rag (spread normally).

### With POROTRINE:

Be taken POROTRINE to the roll diluted for the 1st coat in 1 litre ½ with water.

Cross a 2nd coat diluted in ½ litre of water.

attention: 1st sleeps in the afternoon, 2nd sleeps the following morning.

Definitely work on the roll.

**24 hours afterwards, cross 1 - 2 fine coats of PROCIR SAT to the rag (spread normally).**