

www.porotechnic.com

Zone de Légrin – Route de Saint-Gilles – 30132 CAISSARGUES

04.66.38.38.20 Télécopie : 04.66.38.38.21

S.A.R.L au capital de 50 000 F – SIRET 393122 882 00011

E-mail : contact@porotechnic.com

TREATMENT TILES OF AGED MARBLES

Cleaning:

Having wet tiles in water, passing sour PROCIDEX sulfamique (ancient DK11) Scotchbrite diluted in 1 or 2 litres for 10 litres of water. Rub normally, rinse in the sponge in water 2 - 3 times.

Let dry 2 days.

Treatment POROTRINE:

Wall:

1st kit: Be taken POROTRINE to the brush of bottom above diluted for the 1st coat in 1 litre $\frac{1}{2}$

of water. Definitely wipe castings or drops over joints especially in the 1st coat.

8 hours afterwards

2nd kit: Cross a 2nd coat diluted in $\frac{1}{2}$ litre of water always of bottom above.

Soil:

Be taken POROTRINE to the brush diluted for the 1st coat in 2 litres of water. Slick with one

roll as one goes along without supporting.

24 hours afterwards (never more than 24 hours)

Cross a 2nd coat diluted in 1 litre of water idem the 1st coat

Wait 24 hours for minimum of drying after the 2nd coat

24 hours afterwards, cross 1 - 2 fine coats of PROCIR SAT to the rag (spread normally) to acquire a satiny aspect.

Translation by a generator.